

Using environment-friendly silicate gels to plug near wellbore formations

MARC FLEURY¹, OLIVIER SISSMANN¹, ETIENNE BROSSE¹, MICHEL CHARDIN¹, GUILLAUME BERTHE¹

¹IFP energies nouvelles, Rueil-Malmaison, France

In the framework of the MiReCOL three-year European project, a method for treating the surrounding of a well using a reactive suspension has been studied. Amongst many possible choices, a silicate based product was selected due to the following key qualities: high performance, long term chemical stability (w.r.t. acid), good injectivity (low viscosity and no particles) and no or little environmental impact.

An experimental investigation of the precipitation of commercial low cost potassium silicate solutions was conducted, using a weak acid to lower the pH. In order to estimate the bulk gelation times before the mixture became too viscous for injection, various environment-friendly concentrations of a socially acceptable and non-hazardous acidic compound were added to the silica-based solution. The impact of temperature was determined by performing experiments at 20, 40 and 60°C, with gelation times estimated between a few minutes up to 4 days. The run products were characterized using high resolution physico-chemical techniques, such as rheological visco-elastic properties to observe the gel onset, NMR relaxation time measurements to follow the gradual increase of water interactions within the gel, or infrared spectroscopy to observe the gradual formation of Si-O-Si bonds within the fluid. In addition, the syneresis process (expulsion of water from the gel) was also studied as a function of time and temperature.

The ability of the precipitates to plug a porous media was then tested by injecting an optimum mixture through analog sandstone samples, representative of CO₂ storage formations. Subsequent breakthrough experiments were performed, and so far indicate a very large strength of the order of 600 bar/m. SEM imaging of the plug was then conducted to verify the obstruction of the pore network by the solidified gel. A field-test injection is currently being considered.